



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D21H 17/68	A1	(11) International Publication Number: WO 99/51815 (43) International Publication Date: 14 October 1999 (14.10.99)
(21) International Application Number: PCT/GB99/00888 (22) International Filing Date: 1 April 1999 (01.04.99) (30) Priority Data: 9807180.6 4 April 1998 (04.04.98) GB (71) Applicant (for all designated States except US): ECC INTERNATIONAL LTD. [GB/GB]; 1015 Arlington Business Park, Theale, Reading, Berkshire RG7 4SA (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): HUSBAND, John, Claude [GB/GB]; 32 Parkway, St. Austell, Cornwall PL25 4HR (GB). PAYTON, Desmond, Charles [GB/GB]; 70 Roslyn Close, St. Austell, Cornwall PL25 3UR (GB). RENALS, Michele, Susan [GB/GB]; 24 Eaton Road, St. Austell, Cornwall PL25 3UH (GB). (74) Agent: McCORMACK, Derek, James; ECC International Ltd., Patents Dept., John Keay House, St. Austell, Cornwall PL25 4DJ (GB).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PIGMENT PRODUCTS		
(57) Abstract <p>A pigment product suitable for use in a coating composition to provide a gloss coating on paper, the pigment product comprising a processed particulate kaolin whose particles have a particle size distribution such that at least 80 % by weight of the particles have an equivalent spherical diameter less than 2 μm and not less than 8 %, preferably not less than 12 %, by weight of the particles have an equivalent spherical diameter less than 0.25 μm and whose particles have a shape factor of at least 45, preferably at least 50.</p>		

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

- 1 -

PIGMENT PRODUCTS

The present invention relates to pigment products, and their production and use in coating compositions.

5 The invention concerns the preparation of improved inorganic pigments for paper coating compositions, and, in particular, pigments for use in compositions for preparing gloss coated paper, especially lightweight and ultra lightweight coated paper.

10 Paper coating compositions are generally prepared by forming a fluid aqueous suspension of pigment material together with a hydrophilic adhesive and other optional ingredients. Lightweight coated, or LWC, paper is generally coated to a weight of from about
15 5g.m^{-2} to about 13g.m^{-2} on each side, and the total grammage, or weight per unit area of the coated paper is generally in the range of from about 49g.m^{-2} to about 65g.m^{-2} . The coating may conveniently be applied by means of a coating machine including a short dwell
20 time coating head, which is a device in which a captive pond of coating composition under a slightly elevated pressure is held in contact with a moving paper web for a time in the range of from 0.0004 second to 0.01 second, before excess coating composition is removed by
25 means of a trailing blade. However, other types of coating apparatus may also be used for preparing lightweight coated paper. LWC paper is generally used for printing magazines, catalogues and advertising or promotional material. The coated paper is required to

- 2 -

meet certain standards of surface gloss and smoothness. For example, the paper is generally required to have a gloss value of at least about 32, and up to about 50, TAPPI units, and a Parker Print Surf value in the range
5 of from about $0.5\mu\text{m}$ to about $1.6\mu\text{m}$.

Ultra lightweight coated, or ULWC, paper is sometimes otherwise known as light lightweight coated, or LLWC, paper and is used for catalogues and for advertising and promotional material sent through the
10 mail to reduce mailing costs. The coating weight is generally in the range of from 5g.m^{-2} to 7g.m^{-2} per side. The grammage is generally in the range of from about 35g.m^{-2} to about 48g.m^{-2} .

A very important white inorganic pigment for use
15 in preparing coating compositions for the manufacture of LWC and ULWC papers is kaolin obtained from kaolin clay. Large deposits of kaolin clay exist in Devon and Cornwall, England and in the States of Georgia and South Carolina, United States of America. Important
20 deposits also occur in Brazil, Australia, and in several other countries. Kaolin clay consists predominantly of the mineral kaolinite, together with small proportions of various impurities. Kaolinite exists in the form of hydrous aluminosilicate crystals
25 in the shape of thin hexagonal plates, but these plates tend to adhere together face-to-face to form stacks. The individual plates may have mean diameters of $1\mu\text{m}$ or less, but kaolinite particles in the form of stacks of plates may have an equivalent spherical diameter of up

- 3 -

to 10µm or more. Generally speaking, kaolin clay particles which have an equivalent spherical diameter of 2µm or more are in the form of stacks of kaolinite plates, rather than individual plates.

5 As long ago as 1939, Maloney disclosed in US-A-2158987 that the finish, or gloss, of a clay coated paper is greatly improved if the clay, before incorporation in the coating composition, is treated so that a large percentage, for example 80% by weight or
10 more, of the clay particles have a size in the range of 0.1µm to 2µm. In order to increase the proportion of fine particles in the raw kaolin, the raw kaolin may, according to the disclosure in US-A-2158987, be subjected, before a centrifuging step, to a grinding
15 operation in which a suspension containing from about 50% to about 75% by dry weight of kaolin and a dispersing agent is subjected to pebble milling. When the kaolin from the finer fraction is recovered, mixed with a suitable paper coating binder, and applied to
20 the surface of a base paper, a coating of good gloss and colour is obtained.

Various pigment products which are made using the principles described by Maloney in US-A-2158987 are commercially available and provide good gloss and
25 smoothness in coated papers, especially for LWC and ULWC paper. For example, a pigment product available from the Applicants and recommended for gloss coatings of LWC consists of a refined English kaolin product having a particle size distribution, "psd", such that

- 4 -

89% by weight of the particles have an esd less than 2 μ m, 74% by weight of the particles have an esd less than 1 μ m and 25% by weight of the particles have an esd less than 0.25 μ m.

5 Such commercially available pigment products are not ideal, however. For example, their performance with starch adhesives could be improved. Starches are naturally available from vegetable sources and are the cheapest adhesives for use in coating compositions.

10 However, LWC, ULWC and like papers produced using a coating composition comprising commercially available pigment together with starch suffers from a reduction in gloss compared with similar paper coated with a composition incorporating more expensive synthetic
15 adhesive.

 It is an object of the present invention to provide a pigment product showing improved gloss, particularly but not exclusively when used in a paper coating composition incorporating starch as adhesive or
20 binder ingredient to coat paper to produce LWC, ULWC and other gloss paper products.

 According to the present invention in a first aspect there is provided a pigment product suitable for use in a coating composition to provide a gloss coating
25 on paper, the pigment product comprising a processed particulate kaolin which has a particle size distribution (psd) such that at least 80% by weight of the particles have an equivalent spherical diameter (esd) less than 2 μ m and not less than 8%, preferably

- 5 -

not less than 12% by weight, of the particles have an equivalent spherical diameter (esd) less than $0.25\mu\text{m}$ and whose particles have a shape factor of at least 45.

The pigment product according to the first aspect
5 of the invention unexpectedly and beneficially provides improved gloss when incorporated in coating compositions, especially including starch, for gloss paper coating applications as demonstrated later in this specification.

10 The pigment product according to the first aspect of the invention has an unusual combination of properties which are not normally obtained by conventional processing of kaolin clays from known sources. The reasons for this are as follows.

15 A kaolin product of high shape factor is considered to be more "platey" than a kaolin product of low shape factor. "Shape factor" as used herein is a measure of an average value (on a weight average basis) of the ratio of mean particle diameter to particle
20 thickness for a population of particles of varying size and shape as measured using the electrical conductivity method and apparatus described in GB-A-2240398/US-A-5128606/EP-A-0528078 and using the equations derived in these patent specifications. "Mean particle diameter"
25 is defined as the diameter of a circle which has the same area as the largest face of the particle. In the measurement method described in EP-A-0528078 the electrical conductivity of a fully dispersed aqueous suspension of the particles under test is caused to

- 6 -

flow through an elongated tube. Measurements of the electrical conductivity are taken between (a) a pair of electrodes separated from one another along the longitudinal axis of the tube, and (b) a pair of electrodes separated from one another across the transverse width of the tube, and using the difference between the two conductivity measurements the shape factor of the particulate material under test is determined.

10 The kaolin deposits in England differ from those in the United States of America in that the English deposits are of primary kaolin, whilst those in the USA are of the sedimentary or secondary type. Kaolin was formed in geological times by the hydrothermal decomposition of the feldspar component of granite, and primary kaolin is that which is obtained directly from the granite matrix in which it was originally formed. On the other hand, secondary or (tertiary) kaolin also known as sedimentary kaolin has been washed out of the original granite matrix in geological times and has been deposited in an area remote from the site in which it was originally formed. Secondary kaolin deposits tend to have a higher proportion of fine particles, ie those having an esd smaller than $2\mu\text{m}$, because the kaolin has undergone a certain amount of natural grinding during the course of its transport from its site of origin to its site of final deposition. Jepson (Jepson, W B, "Kaolins: their properties and uses", Phil Trans R Soc Lond, A311, 1984, pp 411-432) has

- 7 -

shown that a sample of an English primary kaolin clay, which has been subjected to a particle size separation such that substantially all particles having an esd larger than $5\mu\text{m}$ have been removed, will comprise

5 particles in the form of roughly hexagonal plates having diameters in the range of from about $8\mu\text{m}$ down to about $0.1\mu\text{m}$, with shape factors which will vary from the coarsest particles to the finest particles the shape factor being from about 20 to about 30. On the

10 other hand, a sample of secondary kaolin clay from Georgia, USA, which has been subjected to a particle size separation such that substantially all particles having an esd larger than $5\mu\text{m}$ have been removed, will typically comprise particles which more nearly conform

15 to a regular hexagonal shape and which has diameters of $0.1\mu\text{m}$ and above, but a generally finer distribution of diameters than is the case with the English kaolin. The shape factor of kaolins of Georgia, USA kaolin presently processed to provide commercial products will

20 often lie within the range of from about 6 to about 10, but there will be little variation in the shape factor with particle diameter.

Thus, the pigment product according to the present invention is not readily derivable from either the

25 kaolins available from England or from Georgia, USA which together are representative of the different kaolins of the world.

The pigment product according to the first aspect of the present invention may be produced by treating a

- 8 -

raw particulate hydrous kaolin mineral of the sedimentary type, and especially a raw or partially processed kaolin clay of the type which occurs in Georgia, USA.

5 The pigment product according to the first aspect of the invention may have a particle size distribution "psd" such that at least 80%, preferably at least 84%, by weight of the particles have an esd smaller than $2\mu\text{m}$ and not less than 12% by weight of the particles,
10 preferably from 15% to 35%, especially 18% to 26%, have an esd smaller than $0.25\mu\text{m}$. Desirably, at least 60%, preferably at least 65% by weight have an esd less than $1\mu\text{m}$. The mean particle esd may be from $0.3\mu\text{m}$ to $0.8\mu\text{m}$, especially from $0.5\mu\text{m}$ to $0.7\mu\text{m}$.

15 As will be appreciated by those skilled in the art, the psd and mean esd of a particulate product such as the pigment product according to the present invention may be determined by measuring the speeds at which dispersed particles of the particulate product
20 under test sediment through a standard dilute aqueous suspension using a SEDIGRAPH™ machine, eg SEDIGRAPH 5100, obtained from Micromeritics Corporation, USA. The size of a given particle is expressed in terms of the diameter of a sphere of equivalent diameter, which
25 sediments through the suspension is expressed as the equivalent spherical diameter or esd, the parameter as referred to above. The SEDIGRAPH machine graphically records the percentage by weight of particles having esd less than a certain esd value versus esd.

- 9 -

Preferably, the percentage by weight of particles having an esd in the range $0.75\mu\text{m}$ to $0.25\mu\text{m}$ of the pigment product according to the first aspect of the invention is 40% or greater, eg from 40% to 50%. The
5 shape factor of the pigment product is preferably at least 50, desirably at least 55, eg 55 to 65.

According to the present invention in a second aspect there is provided a method for producing a pigment product according to the first aspect, the
10 method comprising the steps of:

- (a) mixing a raw or partially processed kaolin clay with water to form an aqueous suspension;
- (b) subjecting the suspension produced by step (a) to attrition grinding using a particulate grinding medium
15 by a process in which the average shape factor of the kaolin clay is increased by at least 10, preferably at least 20;
- (c) separating the suspension of ground kaolin clay from the particulate grinding medium; and
- 20 (d) dewatering the suspension of ground kaolin clay separated in step (c) to recover a kaolin pigment therefrom.

In step (a) of the method according to the second aspect of the present invention, the kaolin clay may
25 form from 20% to 70%, usually from 20% to 45% of the treated suspension. The kaolin clay preferably comprises a sedimentary kaolin clay, most preferably a sedimentary kaolin clay from Georgia, USA. The raw kaolin clay may have a psd such that not more than

- 10 -

about 40% by weight consists of particles having an esd larger than $10\mu\text{m}$ and not more than 50% by weight, eg from about 20% to about 40% by weight, consists of particles having an esd smaller than $2\mu\text{m}$. The shape factor of the kaolin clay treated in step (a) may be
5 less than 15, eg in the range of from about 5 to about 10. Thus, the shape factor may be increased by a differential of at least 30, in some cases at least 40, eg from a shape factor value of less than 15 to a shape
10 factor value greater than 55.

When preparing an aqueous suspension of the kaolin clay to be treated in step (a) a dispersing agent for the kaolin clay may or may not be added to the kaolin clay.

15 The kaolin clay employed in step (a) of the method according to the second aspect may be a coarse component obtained from classifying, eg using a centrifuge, a standard blocky sedimentary kaolin clay, eg having a shape factor of from 5 to 10. The coarse
20 component may have not more than 50% by weight of particles having an esd less than $2\mu\text{m}$ and not more than 10% by weight having an esd less than $0.25\mu\text{m}$.

The psd of the kaolin clay may be adjusted so that it is in accordance with the first aspect of the
25 invention by blending from 99 to 50 parts by weight of the kaolin clay with from 1 to 50 parts by weight, especially from 10 to 30 parts by weight, of a fine platey kaolin component, ie having a shape factor of at least 15, preferably from 15 to 40 and whose

- 11 -

percentages by weight of particles smaller than $2\mu\text{m}$ and $0.25\mu\text{m}$ are respectively at least 85% by weight and at least 20% by weight. The fine platey kaolin component may be a kaolin derived from either a primary or a
5 sedimentary deposit. The fine platey kaolin component may be added to the kaolin of or obtained from the coarse component prior to or after the grinding step (b). The addition may be carried out with the kaolins to be blended in either powdered, dry form or in the
10 form of an aqueous suspension.

We have found that by producing a kaolin product by blending in the manner described, the rheology and dewatering characteristics of an aqueous suspension of the kaolin processed in accordance with the method of
15 the second aspect are improved giving better runnability and particle alignment when the kaolin is used in a coating composition as described later.

The kaolin clay treated in the method according to the second aspect of the invention may be subjected to
20 one or more well known purification steps to remove undesirable impurities, eg between steps (a) and (b). For example, the aqueous suspension of kaolin clay may be subjected to a froth flotation treatment operation to remove titanium containing impurities in the froth.
25 Alternatively, or in addition, the suspension may be passed through a high intensity magnetic separator to remove iron containing impurities.

Step (b) may comprise a process wherein the suspension of kaolin clay is treated by medium

- 12 -

attrition grinding wherein an energy of from about 40kWh to about 250kWh per tonne of clay (on a dry weight basis) is dissipated in the suspension.

The process of step (b) may itself comprise a
5 process comprising at least two stages, namely a first stage (b1) wherein delamination of the kaolin clay occurs and a second stage (b2) wherein comminution of the platelets of the kaolin clay occurs.

Thus, it has been found to be beneficial to
10 subject the suspension of the kaolin clay to a relatively gentle comminution step (b1), eg grinding using a particulate grinding medium in order to break down composite particles which are present in the raw kaolin clay. Such composite particles generally
15 comprise coherent stacks or blocks of individual hexagonal plate-like particles, especially where the kaolin clay is from a sedimentary deposit. When the kaolin clay is subjected to relatively gentle comminution, eg by grinding in step (b1), the composite
20 particles are broken down to give the individual thin, substantially hexagonal plates. Such a process is generally well known in the art and is referred to as "delamination", and has the result of increasing the average shape factor of the kaolin clay. For example,
25 this process may increase the shape factor of the kaolin clay from a starting shape factor of about 5 to 10 to an increased shape factor of at least about 50 to 55. By "relatively gentle grinding" we mean grinding in an attrition grinding mill with a particulate

- 13 -

grinding medium, the contents of the attrition grinding mill being agitated by means of an impeller which rotates at a speed which is insufficient to set up a vortex in the suspension, ie at a peripheral speed
5 below about 10m.s^{-1} and in which the amount of energy dissipated in the suspension during grinding is less than about 75kWh, usually less than about 55kWh per tonne of kaolin clay on a dry weight basis. The particulate grinding medium is preferably of relatively
10 high specific gravity, for example 2 or more, and may for example comprise grains of silica sand, the grains generally having diameters not larger than about 2mm and not smaller than about 0.25mm.

In stage (b2) of the two stage form of step (b) in
15 the method according to the second aspect, the grinding is preferably performed in an attrition grinding mill which is equipped with a stirrer which is capable of being rotated at a speed such that a vortex is formed in the suspension in the mill during grinding. Again,
20 the particulate grinding medium preferably has a specific gravity of 2 or more, and advantageously comprises grains of silica sand the grains generally having diameters not larger than about 2mm and not smaller than about 0.25mm. If stage (b2) is preceded
25 by a relatively gentle comminution in stage (b1), the amount of energy dissipated in the suspension of kaolin clay in stage (b2) is preferably in the range of from about 40kWh to about 120kWh per dry tonne of kaolin clay. However, if the relatively gentle comminution

- 14 -

step (b1) is omitted, the amount of energy dissipated in the suspension of kaolin clay in step (b) is preferably in the range of from about 100kWh to about 250kWh per dry tonne of kaolin clay.

5 In step (c) of the method according to the second aspect of the invention, the suspension of ground kaolin clay is conveniently separated from the particulate grinding medium in a known manner, eg by passing the suspension through a sieve of appropriate
10 aperture size, for example a sieve having nominal aperture sizes in the range of from about 0.1mm to about 0.25mm.

 Following step (c) or step (d) the kaolin clay may be further treated to improve one or more of its
15 properties. For example high energy liquid working, eg using a high speed mixer, may be applied to the product in slurry form, eg before step (d) or after step (d) and subsequent re-dispersion in an aqueous medium, eg during makedown of a coating composition.

20 In step (d) of the method according to the second aspect of the invention, the suspension of ground kaolin may be dewatered in one of the ways well known in the art, eg filtration, centrifugation, evaporation and the like. Dewatering using a filter press is
25 preferred. For example, use of a filter press may be made to form a cake having a water content in the range of from about 15% to about 35% by weight. This cake may be mixed with a dispersing agent for the kaolin clay and thus converted into a fluid slurry which may

- 15 -

be transported and sold in this form. Alternatively, the kaolin clay may be thermally dried, for example by introducing the fluid slurry of the kaolin clay into a spray drier and thereby transported in a substantially dry form.

A fine platey kaolin component may be blended with the product of step (d) in the manner described earlier if such a component has not already been added prior to step (d).

10 The pigment product according to the first aspect of the invention may have a specific surface area as measured by the BET, N_2 method of at least $12\text{m}^2.\text{g}^{-1}$, preferably from $15\text{m}^2.\text{g}^{-1}$ to $20\text{m}^2.\text{g}^{-1}$.

15 The pigment product according to the first aspect of the present invention may be used in paper coating as follows.

According to the present invention in a third aspect there is provided a coating composition for use in producing gloss coatings on paper and other
20 substrates which composition comprises an aqueous suspension of a particulate pigment together with a hydrophilic adhesive or binder, wherein the particulate pigment comprises the pigment product according to the first aspect of the invention.

25 The solids content of the paper coating composition according to the third aspect of the invention may be greater than 60% by weight, preferably at least 70%, preferably as high as possible but still giving a suitably fluid composition which may be used

- 16 -

in coating. The composition may include a dispersing agent, eg up to 2% by weight of a polyelectrolyte based on the dry weight of pigment present. For example, polyacrylates and copolymers containing polyacrylate units are well known as suitable polyelectrolytes. The pigment product according to the first aspect of the invention may be used as the sole pigment in the paper coating composition according to the third aspect, or it may be used in conjunction with one or more other known pigments, such as for example, (commercially available) kaolin, calcined kaolin, natural or precipitated calcium carbonate, titanium dioxide, calcium sulphate, satin white, talc and so called 'plastic pigment'. When a mixture of pigments is used the pigment product according to the first aspect of the invention is preferably present in the mixture in an amount of at least 80% of the total dry weight of the mixed pigments.

The binder of the composition according to the third aspect may conveniently comprise an adhesive derived from natural starch obtained from a known plant source, for example, wheat, maize, potato or tapioca although it is not essential to use starch as a binder ingredient. Other binders, which may be used with or without starch are mentioned later.

Where starch is employed as a binder ingredient, the starch may be unmodified or raw starch, or it may be modified by one or more chemical treatments known in the art. The starch may, for example, be oxidised to

- 17 -

convert some of its $-CH_2OH$ groups to $-COOH$ groups. In some cases the starch may have a small proportion of acetyl, $-COCH_3$, groups. Alternatively, the starch may be chemically treated to render it cationic or

5 amphoteric, ie with both cationic and anionic charges. The starch may also be converted to a starch ether, or hydroxyalkylated starch by replacing some $-OH$ groups with, for example, $-O.CH_2.CH_2OH$ groups, $-O.CH_2.CH_3$ groups or $-O.CH_2.CH_2.CH_2OH$ groups. A further class of

10 chemically treated starches which may be used is that known as the starch phosphates. Alternatively, the raw starch may be hydrolysed by means of a dilute acid or an enzyme to produce a gum of the dextrin type. The amount of the starch binder used in the composition

15 according to the third aspect is preferably from 4% to 25% by weight, based on the dry weight of pigment. The starch binder may be used in conjunction with one or more other binders, for example synthetic binders of the latex or polyvinyl acetate or polyvinyl alcohol

20 type. When the starch binder is used in conjunction with another binder, eg a synthetic binder, the amount of the starch binder is preferably from 2% to 20% by weight, and the amount of the synthetic binder from 2% to 12% by weight, both based on the weight of dry

25 pigment. Preferably, at least 50% by weight of the binder mixture comprises modified or unmodified starch.

According to the present invention in a fourth aspect there is provided a method of use of the coating composition according to the third aspect which

- 18 -

comprises applying the composition to coat a sheet of paper and calendering the paper to form a gloss coating thereon. Preferably, the gloss coating is formed on both sides of the paper.

- 5 Calendering is a well known process in which paper smoothness and gloss is improved and bulk is reduced by passing a coated paper sheet between calender nips or rollers one or more times. Usually, elastomer coated rolls are employed to give pressing of high solids
- 10 compositions. An elevated temperature may be applied. Five or more passes through the nips may be applied.

The paper after coating and calendering in the method according to the fourth aspect may have a total weight per unit area in the range 30g.m^{-2} to 70g.m^{-2} ,
15 especially 49g.m^{-2} to 65g.m^{-2} or 35g.m^{-2} to 48g.m^{-2} . The final coating preferably has a weight per unit area preferably from 3g.m^{-2} to 20g.m^{-2} , especially from 5g.m^{-2} to 13g.m^{-2} . Such a coating may be applied to both sides of the paper. Thus, the coated paper may be LWC
20 or ULWC paper. The paper gloss may be greater than 45 TAPPI units and the Parker Print Surf value at a pressure of 1MPa of each paper coating may be less than $1\mu\text{m}$.

The gloss of a coated paper surface may be
25 measured by means of a test laid down in TAPPI Standard No 480 ts-65. The intensity of light reflected at an angle from the surface of the paper is measured and compared with a standard of known gloss value. The beams of incident and reflected light are both at an

- 19 -

angle of 75° to the normal to the paper surface. The results are expressed in TAPPI gloss units. The gloss of the pigment product according to the first aspect may be greater than 50, in some cases greater than 55, 5 TAPPI units.

The Parker Print Surf test provides a measure of the smoothness of a paper surface, and comprises measuring the rate at which air under pressure leaks from a sample of the coated paper which is clamped, 10 under a known standard force, between an upper plate which incorporates an outlet for the compressed air and a lower plate, the upper surface of which is covered with a sheet of either a soft or a hard reference supporting material according to the nature of the 15 paper under test. From the rate of escape of the air, a root mean cube gap in μm between the paper surface and the reference material is calculated. A smaller value of this gap represents a higher degree of smoothness of the surface of the paper under test.

20 As noted above, an improvement is provided by the present invention where the binder present in the coating composition according to the third aspect comprises starch. However, an improvement is also obtained where other known starch-free binders are 25 employed (with or without starch present). In each case the adhesive or binder may form from 4% to 30%, eg 8% to 20%, especially 8% to 15% by weight of the solids content of the composition. The amount employed will depend upon the composition and the type of adhesive,

- 20 -

which may itself incorporate one or more ingredients. For example, hydrophilic adhesives used in the art, eg incorporating one or more of the following adhesive or binder ingredients may be used in the following stated amounts:

- (a) latex: levels range from 4% by weight to 20% by weight. The latex may comprise for example a styrene butadiene, acrylic latex, vinyl acetate latex, or styrene acrylic copolymers.
- 10 (b) other binders: levels again range from eg 4% by weight to 20% by weight. Examples of other binders include casein, polyvinyl alcohol and polyvinyl acetate.

Additives in various known classes may, depending upon the type of coating and material to be coated, be included in the coating composition according to the third aspect of the present invention. Examples of such classes of optional additive are as follows:

- (a) cross linkers: eg in levels of up to 5% by weight; for example glyoxals, melamine formaldehyde resins, ammonium zirconium carbonates.
- (b) water retention aids: eg in up to 2% by weight, for example sodium carboxymethyl cellulose, hydroxyethyl cellulose, PVA (polyvinyl acetate), starches, proteins, polyacrylates, gums, alginates, polyacrylamide bentonite and other commercially available products sold for such applications.
- (c) viscosity modifiers or thickeners: eg in levels up to 2% by weight; for example polyacrylates, emulsion

- 21 -

copolymers, dicyanamide, triols, polyoxyethylene ether, urea, sulphated castor oil, polyvinyl pyrrolidone, montmorillonite, CMC (carboxymethyl celluloses), sodium alginate, xanthan gum, sodium silicate, acrylic acid
5 copolymers, HMC (hydroxymethyl celluloses), HEC (hydroxyethyl celluloses) and others.

(d) lubricity/calendering aids: eg in levels up to 2% by weight, for example calcium stearate, ammonium stearate, zinc stearate, wax emulsions, waxes, alkyl
10 ketene dimer, glycols.

(e) dispersants: eg in levels up to 2 per cent by weight, for example polyelectrolytes such as polyacrylates and copolymers containing polyacrylate species, especially polyacrylate salts (eg sodium and
15 aluminium optionally with a group II metal salt), sodium hexametaphosphates, non-ionic polyol, polyphosphoric acid, condensed sodium phosphate, non-ionic surfactants, alkanolamine and other reagents commonly used for this function.

(f) antifoamers/defoamers: eg in levels up to 1% by weight, for example blends of surfactants, tributyl phosphate, fatty polyoxyethylene esters plus fatty alcohols, fatty acid soaps, silicone emulsions and
25 other silicone containing compositions, waxes and inorganic particulates in mineral oil, blends of emulsified hydrocarbons and other compounds sold commercially to carry out this function.

(g) dry or wet pick improvement additives: eg in levels up to 2% by weight, for example melamine resin,

- 22 -

polyethylene emulsions, urea formaldehyde, melamine formaldehyde, polyamide, calcium stearate, styrene maleic anhydride and others.

(h) dry or wet rub improvement and abrasion resistance
5 additives: eg in levels up to 2% by weight, for example glyoxal based resins, oxidised polyethylenes, melamine resins, urea formaldehyde, melamine formaldehyde, polyethylene wax, calcium stearate and others.

(i) gloss-ink hold-out additives: eg in levels up to
10 2% by weight, for example oxidised polyethylenes, polyethylene emulsions, waxes, casein, guar gum, CMC, HMC, calcium stearate, ammonium stearate, sodium alginate and others.

(j) optical brightening agents (OBA) and fluorescent
15 whitening agents (FWA): eg in levels up to 1% by weight, for example stilbene derivatives.

(k) dyes: eg in levels up to 0.5% by weight.

(l) biocides/spoilage control agents: eg in levels up
to 1% by weight, for example metaborate, sodium
20 dodecylbenene sulphonate, thiocyanate, organosulphur, sodium benzonate and other compounds sold commercially for this function eg the range of biocide polymers sold by Calgon Corporation.

(m) levelling and evening aids: eg in levels up to 2%
25 by weight, for example non-ionic polyol, polyethylene emulsions, fatty acid, esters and alcohol derivatives, alcohol/ethylene oxide, sodium CMC, HEC, alginates, calcium stearate and other compounds sold commercially for this function.

- 23 -

(n) grease and oil resistance additives: eg in levels up to 2% by weight, eg oxidised polyethylenes, latex, SMA (styrene maleic anhydride), polyamide, waxes, alginate, protein, CMC, HMC.

5 (o) water resistance additives: eg in levels up to 2% by weight, eg oxidised polyethylenes, ketone resin, anionic latex, polyurethane, SMA, glyoxal, melamine resin, urea formaldehyde, melamine formaldehyde, polyamide, glyoxals, stearates and other materials
10 commercially available for this function.

(p) insolubiliser: eg in levels up to 2% by weight.

For all of the above additives, the percentages by weight quoted are based on the dry weight of pigment (100%) present in the composition. Where the additive
15 is present in a minimum amount the minimum amount may be 0.01% by weight based on the dry weight of pigment.

The method according to the fourth aspect of the present invention may be carried out in a known way which will depend upon the material to be coated, the
20 coating composition to be applied and other factors as determined by the operator, eg speed and ease of runnability eg using a conventional coating machine.

Methods of coating paper and other sheet materials are widely published and well known. For example,
25 there is a review of such methods published in Pulp and Paper International, May 1994, page 18 et seq. Sheets may be coated on the sheet forming machine, ie. "on-machine", or "off-machine" on a coater or coating machine. Use of high solids compositions is desirable

- 24 -

in the coating method because it leaves less water to evaporate subsequently. However, as is well known in the art, the solids level should not be so high that high viscosity and levelling problems are introduced.

5 All known methods of coating for use in step (b) of the method according to the fourth aspect of the present invention require (i) a means of applying the coating composition to the material to be coated, viz an applicator; and (ii) a means for ensuring that a
10 correct level of coating composition is applied, viz a metering device. When an excess of coating composition is applied to the applicator, the metering device is downstream of it. Alternatively, the correct amount of coating composition may be applied to the applicator by
15 the metering device, eg as a film press. At the points of coating application and metering, the paper web support ranges from a backing roll, eg via one or two applicators, to nothing (ie: just tension). The time the coating is in contact with the paper before the
20 excess is finally removed is the dwell time - and this may be short, long or variable.

The coating is usually added by a coating head at a coating station. According to the quality desired, paper grades are uncoated, single coated, double coated
25 and even triple coated. When providing more than one coat, the initial coat (precoat) may have a cheaper formulation and optionally less pigment in the coating composition. A coater that is applying a double coating, ie. a coating on each side of the paper, will

- 25 -

have two or four coating heads, depending on the number of sides coated by each head. Most coating heads coat only one side at a time, but some roll coaters (eg film press, gate roll, size press) coat both sides in one
5 pass.

Examples of known coaters which may be employed in step (b) include air knife coaters, blade coaters, rod coaters, bar coaters, multi-head coaters, roll coaters, roll/blade coaters, cast coaters, laboratory coaters,
10 gravure coaters, kiss coaters, liquid application systems, reverse roll coaters and extrusion coaters.

In all examples of coating compositions described in this specification, water is added to the solids to give a concentration of solids which when coated onto a
15 sheet to a desired target coat weight has a rheology suitable for the composition to be coated with a pressure (eg a blade pressure) of between 1 and 1.5 bar. Generally, the solids content may be from 60% to 70% by weight.

20 Embodiments of the present invention will now be described by way of example with reference to the following illustrative Examples.

EXAMPLE 1

25 A raw kaolin clay from a sedimentary deposit in Georgia, USA was suspended in water and the resultant suspension was passed through a high intensity magnetic separator to remove iron-containing impurities therefrom. After the magnetic separation step the

- 26 -

kaolin clay was found to have a psd such that 30% by weight consisted of particles having an esd smaller than $2\mu\text{m}$, and 7.0% by weight consisted of particles having an esd smaller than $0.25\mu\text{m}$. The shape factor of the kaolin clay as measured by the method described in GB-A-2240398 was found to be 6.8.

The suspension of kaolin clay was then subjected to relatively gentle attrition grinding in a grinding chamber provided with a submerged internal impeller, the speed of rotation of which was insufficient to form a vortex in the suspension contained in the grinding chamber. The grinding medium was a silica sand having grains in the size range from 0.6mm to 0.85mm. The grinding was continued for a time such that the amount of energy dissipated in the suspension was 50.7kWh per tonne of kaolin clay (on a dry weight basis). At the completion of this grinding step, the kaolin clay was found to have a psd such that 71.2% by weight consisted of particles having an esd smaller than $2\mu\text{m}$ and 5.0% by weight consisted of particles having an esd smaller than $0.25\mu\text{m}$. The mean particle shape factor as measured by the method described in GB-A-2240398 was found to be 52.

The suspension of ground kaolin clay was separated from the grinding medium by elutriation and was then subjected to a second stage of attrition grinding in a grinding chamber equipped with a high-speed impeller which was capable of generating a vortex in the suspension contained in the chamber. The grinding

- 27 -

medium used was Ottawa sand, a relatively pure silica sand with rounded grains, having a distribution of grain sizes between 0.5 and 1.0mm. The solids concentration of the suspension was 27% by weight based on the dry weight of the kaolin clay. The grinding chamber was operated continuously in closed cycle with a hydrocyclone which separated sufficiently ground particles as product and returned insufficiently ground particles to the grinding chamber. The suspension of ground kaolin clay was discharged continuously through apertures high in the side walls of the grinding chamber, these apertures being covered with sieves of nominal aperture 0.25mm to hold back the grains of the grinding medium. The suspension of ground kaolin clay passing through the sieves was collected in a trough surrounding the grinding chamber, from whence it was pumped under pressure to the hydrocyclone.

Samples A, B and C of the suspension of the ground kaolin clay were withdrawn from the recirculating system after times sufficient to dissipate in the suspension, respectively, 40kWh, 60kWh and 80kWh of energy per tonne of kaolin clay (on a dry weight basis). The percentages by weight of particles in the products having esds larger than 10 μ m, smaller than 2 μ m, smaller than 1 μ m and smaller than 0.25 μ m, respectively, and the mean particle shape factors of the products were measured. The results are set forth in Table 1 as follows.

- 28 -

TABLE 1

Sample	Energy dissipated (kWh.tonne ⁻¹)	% by weight of particles.				Mean particle shape factor
		Larger than 10µm	Smaller than 2µm	Smaller than 1µm	Smaller than 0.25µm	
A	40	1.3	87.2	66.8	8.0	56.8
B	60	0.2	89.9	72.6	17.9	60.0
C	80	0.4	92.2	76.8	20.8	68.4

EXAMPLE 2

A further sample of the same raw kaolin from Georgia, USA as was used in Example 1 was suspended in water to form an aqueous suspension containing 23.5% by weight of kaolin clay on a dry weight basis. Without preliminary magnetic separation treatment, this suspension was introduced into a recirculating attrition grinding system of the same type as that described in connection with the second stage of grinding in Example 1 above. Grinding was continued, with recirculation of insufficiently ground material, for a time sufficient to dissipate in the suspension 210kWh of energy per tonne of the kaolin clay on a dry weight basis. After this time the ground kaolin clay was recovered from the suspension by filtration and subsequent thermal drying and was found to have a psd such that 0.2% by weight consisted of particles having an esd larger than 10µm, 89.9% by weight consisted of particles having an esd smaller than 2µm, 72.6% by

- 29 -

weight consisted of particles having an esd smaller than 1µm and 17.9% by weight consisted of particles having an esd smaller than 0.25µm. The shape factor of the product was 59.7.

5

EXAMPLE 3

Ground kaolin product Sample C produced in Example 1 above was used as a pigment in a coating composition used for preparing an ULWC for offset printing. The
10 coating composition had the composition shown in Table 2 as follows.

TABLE 2

Ingredient	Parts by weight
Pigment under test	88
Calcined kaolin	10
Titanium dioxide	2
Starch binder	12
Synthetic latex binder	6

15 The calcined kaolin had a particle size distribution such that 90% by weight consisted of particles having an esd smaller than 2µm.

The starch binder was a hydroxyethyl ether of corn starch which is marketed under the trade name "PENFORD
20 GUM 290".

The synthetic latex binder was a styrene butadiene rubber binder of the type which has been found to be suitable for use in offset coating formulations. The

- 30 -

parts by weight shown are parts by weight of latex solids.

The ground kaolin product C in accordance with an embodiment of the invention was compared with two
5 commercially available products, namely commercially available pigments 1 and 2, which were each separately made into the composition shown in Table 2 above.

Commercially available pigment 1 was a delaminated kaolin clay from Georgia, USA having a particle size
10 distribution such that 81.5% by weight consisted of particles having an esd smaller than $2\mu\text{m}$, 62.5% by weight consisted of particles having an esd smaller than $1.0\mu\text{m}$ and 20% consisted of particles having an esd smaller than $0.25\mu\text{m}$. The shape factor of the product
15 was 29.

Commercially available pigment 2 was a fine English kaolin clay having a psd such that 89% by weight consisted of particles having an esd smaller than $2\mu\text{m}$, 74% by weight consisted of particles having
20 an esd smaller than $1\mu\text{m}$ and 25% by weight consisted of particles having an esd smaller than $0.25\mu\text{m}$. The particle shape factor of the product was 31.

Each composition under test was coated onto base paper of substance weight 30g.m^{-2} by means of a coating
25 machine of the type described in GB-A-1032536 fitted with a short dwell time head. The paper speed was 1100m.min^{-1} . Samples of a coated paper were prepared at different coat weights in the range of from about 4g.m^{-2} to about 7g.m^{-2} . The coated paper was dried and

- 31 -

then subjected to calendering by passage ten times between the rolls of a supercalender at a temperature of 80°C and a pressure of 7MPa.

The samples of calendered coated paper prepared from each of the three coating compositions were then tested for gloss according to TAPPI Standard No 480 ts-65, brightness, or percentage reflectance to light of a 457nm wavelength, and Parker Print Surf using the soft backing material and a pressure of 1000kPa. In each case the measured values were plotted graphically against coat weight, and the value which corresponded to a coat weight of 6g.m⁻² was found by interpolation.

The results are set forth in Table 3 as follows.

15 TABLE 3

Pigment	Gloss (TAPPI units)	% reflectance to light of 457nm wavelength	Parker Print Surf 1000kPa
Pigment in accordance with an embodiment of the invention	47	69.8	0.83
Commercially available pigment 1	38	67.9	0.98
Commercially available pigment 2	40	68.6	1.13

It can be seen from Table 3 that the pigment in accordance with an embodiment of the invention provides an ULWC paper, suitable for use in offset printing,

- 32 -

which paper has considerably improved gloss, brightness and smoothness as compared with coated papers which have been prepared using commercially available pigments which are generally recommended for preparing coated papers of this type. It will be noted, in particular, that commercially available pigment 2 has a particle size distribution which closely resembles that of the pigment in accordance with the invention, and it would generally be expected that this pigment would have approximately equal performance to that of the pigment in accordance with the invention when used as a pigment in a paper coating composition. However, the pigment in accordance with an embodiment of the invention is seen to be superior even to this fine commercially available pigment.

EXAMPLE 4

A raw kaolin from a sedimentary deposit in Georgia, US was suspended in water and the resultant suspension was degrittled, treated with a dispersing agent, and classified in a decanter centrifuge under conditions such that the overflow product produced by the centrifuge had a psd such that about 90% by weight of the particles had an esd smaller than $2\mu\text{m}$. The underflow product of the centrifuge was passed through a high intensity magnetic separator to remove iron-containing impurities and the magnetically purified product suspension was then subjected to attrition grinding using silica sand as a grinding medium. The

- 33 -

suspension of ground kaolin particles was then subjected to a second stage of classification in a decanter centrifuge. The overflow product from this centrifuge had a particle size distribution such that
5 84% by weight of the particles had an esd smaller than $2\mu\text{m}$, and the underflow product was used as the feed for the next stage in the process.

This second underflow product was found to have a psd such that 9% by weight consisted of particles
10 having an esd larger than $10\mu\text{m}$, 28% by weight consisted of particles having an esd smaller than $2\mu\text{m}$ and 4% by weight consisted of particles having an esd smaller than $0.25\mu\text{m}$. The shape factor of this underflow product as measured by the method described in GB-A-
15 2240398 was found to be 28.

The suspension of kaolin clay was then subjected to relatively gentle attrition grinding in a grinding chamber provided with a submerged internal impeller, the speed of rotation of which was insufficient to form
20 a vortex in the suspension contained in the grinding chamber. The grinding medium was a silica sand having grains in the size range from 0.6mm to 0.85 mm. The grinding was continued for a time such that the amount of energy dissipated in the suspension was 30.9 kWh per
25 tonne of dry kaolin clay. At the completion of this grinding step, the kaolin clay was found to have a psd such that 3% by weight consisted of particles having an esd larger than $10\mu\text{m}$, 47% by weight consisted of particles having an esd smaller than $2\mu\text{m}$ and 5% by

- 34 -

weight consisted of particles having an esd smaller than $0.25\mu\text{m}$. The shape factor of the kaolin clay after grinding as measured by the method described in GB-A-2240398, was found to be 65.9.

5 The suspension of ground kaolin clay was separated from the grinding medium by elutriation and was then classified in a decanter centrifuge under conditions such that the overflow product produced by the centrifuge had a psd such that 90% by weight of the
10 particles had an esd smaller than $2\mu\text{m}$. The overflow product from the centrifuge was then acidified with sulphuric acid, bleached with 3kg of sodium dithionite bleaching reagent per dry tonne of kaolin, dewatered in a filterpress, and the cake thus formed was redispersed
15 with the aid of 0.25% by weight, based on the dry weight of kaolin, of a sodium polyacrylate dispersing agent. The dispersed suspension was then spray dried to form a dry powder.

 The final kaolin clay product had a psd such that
20 89% by weight consisted of particles having an esd smaller than $2\mu\text{m}$, 69% by weight consisted of particles having an esd smaller than $1\mu\text{m}$ and 18% by weight consisted of particles having an esd smaller than $0.25\mu\text{m}$. The shape factor as measured by the method
25 described in GB-A-2240398 was found to be 65.

 This product was identified as ground kaolin product D.

- 35 -

EXAMPLE 5

A raw kaolin from a sedimentary deposit in Georgia, US was suspended in water and the resultant suspension was degrittied, treated with a dispersing agent, and classified in a decanter centrifuge under conditions such that the overflow product produced by the centrifuge had a psd such that 90% by weight of the particles had an esd smaller than $2\mu\text{m}$. The underflow product of the centrifuge was passed through a high intensity magnetic separator to remove iron-containing impurities and the magnetically purified product suspension was then subjected to attrition grinding using silica sand as a grinding medium. The suspension of ground kaolin particles was then subjected to a second stage of classification in a decanter centrifuge. The overflow product from this centrifuge had a psd such that 84% by weight of the particles had an esd smaller than $2\mu\text{m}$, and the underflow product was used as the feed for the next stage in the process.

This second underflow product was found to have a psd such that 8% by weight consisted of particles having an esd larger than $10\mu\text{m}$, 30% by weight consisted of particles having an esd smaller than $2\mu\text{m}$ and 4% by weight consisted of particles having an equivalent spherical diameter smaller than $0.25\mu\text{m}$. The shape factor of this underflow product as measured by the method described in GB-A-2240398 was found to be 36.

The suspension of kaolin clay was then subjected to relatively gentle attrition grinding in a grinding

- 36 -

chamber provided with a submerged internal impeller, the speed of rotation of which was insufficient to form a vortex in the suspension contained in the grinding chamber. The grinding medium was a silica sand having
5 grains in the size range from 0.6mm to 0.85 mm. The grinding was continued for a time such that the amount of energy dissipated in the suspension was 17.2 kWh per tonne of dry kaolin clay. At the completion of this grinding step, the kaolin clay was found to have a psd
10 such that 5% by weight consisted of particles having an esd larger than $10\mu\text{m}$, 41% by weight consisted of particles having an esd smaller than $2\mu\text{m}$ and 5% by weight consisted of particles having an esd smaller than $0.25\mu\text{m}$. The particle shape factor after grinding,
15 as measured by the method described in GB-A-2240398, was found to be 48.5.

The suspension of ground kaolin clay was separated from the grinding medium by elutriation and was then classified in a decanter centrifuge under conditions
20 such that the overflow product produced by the centrifuge had a psd such that 90% by weight of the particles had an esd smaller than $2\mu\text{m}$. The overflow product from the centrifuge was then acidified with sulphuric acid, bleached with 3kg of sodium dithionite
25 bleaching reagent per tonne of dry kaolin, dewatered in a filterpress, and the cake thus formed was redispersed with the aid of 0.25% by weight, based on the weight of dry kaolin, of a sodium polyacrylate dispersing agent.

- 37 -

The dispersed suspension was then spray dried to form a dry powder.

The final kaolin clay product had a psd such that 90% by weight consisted of particles having an esd smaller than $2\mu\text{m}$, 72% by weight consisted of particles having an esd smaller than $1\mu\text{m}$ and 21% by weight consisted of particles having an esd smaller than $0.25\mu\text{m}$. The shape factor of the product as measured by the method described in GB-A-2240398 was found to be 54.

This product was identified as ground kaolin product E.

EXAMPLE 6

A typical paper coating composition of the type used for preparing a coated paper for rotogravure printing had the composition as shown in Table 4 as follows:

TABLE 4

Ingredient	Parts by weight
Pigment under test	90
Calcined kaolin	10
Synthetic latex binder	6
Synthetic acrylic thickener	0.2
Sodium hydroxide to pH 8	

The calcined kaolin was the same as that used in Example 3.

- 38 -

The synthetic latex binder was a styrene butadiene rubber binder of the type which has been found to be suitable for use in rotogravure coating formulations. The parts by weight shown are parts by weight of latex solids.

Paper coating compositions were prepared according to the formulation specified in Table 4 containing as the pigment under test, respectively:

Composition 1): (i) 75 parts by weight of ground kaolin product D prepared as described in Example 4; and (ii) 15 parts by weight of a commercially available, high quality paper coating-grade English kaolin having a psd such that 89% by weight consisted of particles having an esd smaller than $2\mu\text{m}$, 75% by weight consisted of particles having an esd smaller than $1\mu\text{m}$ and 25% by weight consisted of particles having an esd smaller than $0.25\mu\text{m}$, and a mean particle shape factor of 35.

Composition 2): (i) 75 parts by weight of ground kaolin product D prepared as described in Example 4; and (ii) 15 parts by weight of a high quality commercially available paper coating-grade kaolin from Georgia, US having a psd such that 95% by weight consisted of particles having an esd smaller than $2\mu\text{m}$, 91% by weight consisted of particles having an esd smaller than $1\mu\text{m}$ and 52% by weight consisted of particles having an esd smaller than $0.25\mu\text{m}$, and a shape factor of 17.

- 39 -

Each composition was coated onto a web of base paper of substance weight 31g.m^{-2} by means of a pilot paper coating machine fitted with a short dwell time head. The paper speed was 1100m.min^{-1} and the blade angle was 45° . The solids concentration of the coating composition was adjusted so that the pressure of the hydraulic fluid supplied to a pressurisable tube used for biasing the blade against the web of paper was in the range of from 1.0 to 1.5 bar in order to provide the desired coat weight. The dry weight of the coating applied to the web of paper was in each case 6g.m^{-2} . The coated paper was dried and then subjected to calendering by passage ten times between the rolls of a pilot-scale supercalender at a temperature of 80°C and a linear pressure of 230kN.m^{-1} .

The samples of calendered coated paper were then tested for gloss, brightness and Parker Print Surf by the methods which were described in Example 3.

Samples of paper coated with the different coating compositions were also tested for gravure print quality by methods described in the article "Realistic paper tests for various printing processes" by A Swan, published in "Printing Technology", Vol 13, No 1, April 1969, pages 9-22. A gravure printing cylinder was used with an area of deeply etched cells to give a solid black area, and an area of less deeply etched cells to give a half-tone area. The half-tone area was used to estimate the percentage of gravure dots which were missing from the test print. This percentage was

- 40 -

expressed as "% missing dots". The solid black area was used to measure the gravure print density using a Macbeth density meter.

The results obtained are set forth in Table 5 as follows.

TABLE 5

Pigment	Gloss (TAPPI units)	% reflectance to light of 457nm wavelength	Parker Print Surf 1000 kPa	% missing dots
Composition 1	56	70.5	0.97	7.5
Composition 2	53	69.6	0.98	9

The results in Table 5 show that when 75 parts by weight of a de-fined, high shape factor kaolin produced by method embodying the second aspect of the invention were blended with 15 parts by weight of a fine kaolin clay having a relatively high shape factor of 35 (Composition 1), the coated paper showed a higher gloss and brightness, and a better gravure print quality. Paper which had been coated with a composition containing 75 parts by weight of the same de-fined, high shape factor kaolin employed in Composition 1 and 5 parts by weight of a kaolin clay having a relatively low shape factor of 17 (Composition 2) also showed acceptable properties. The smoothness of the coated paper was substantially the same in the two cases.

- 41 -

EXAMPLE 7.

Further paper coating compositions were prepared according to the formulations given in Example 6 earlier.

5 In these compositions, the pigments under test were, respectively:

Composition 3): (i) 55 parts by weight of ground kaolin product D, prepared as described in Example 4; 20 parts by weight of ground kaolin product E, prepared as described in Example 5, and (ii) 15 parts by weight of the same English, high quality paper coating-grade kaolin as was used in Example 6.

Composition 4): (i) 55 parts by weight of ground kaolin product D, prepared as described in Example 4; 15 (ii) 20 parts by weight of ground kaolin product E, prepared as described in Example 5, and (iii) 15 parts by weight of a high quality paper coating-grade kaolin from Georgia, US having a psd such that 97% by weight consisted of particles having an esd smaller than $2\mu\text{m}$, 20 91% by weight consisted of particles having an esd smaller than $1\mu\text{m}$ and 44% by weight consisted of particles having an esd smaller than $0.25\mu\text{m}$, and a shape factor of 30.

Composition 5): (i) 55 parts by weight of ground 25 kaolin product D, prepared as described in Example 4; (ii) 20 parts by weight of ground kaolin product E, prepared as described in Example 5, and (iii) 15 parts by weight of a No 2 paper coating-grade kaolin from Georgia, US having a psd such that 84% by weight

- 42 -

consisted of particles having an esd smaller than $2\mu\text{m}$,
70% by weight consisted of particles having an esd
smaller than $1\mu\text{m}$ and 25% by weight consisted of
particles having an esd smaller than $0.25\mu\text{m}$, and a
5 shape factor of 12.

Each composition was coated onto a web of base
paper of substance weight 31g.m^{-2} by means of a pilot
paper coating machine fitted with a short dwell time
head. The paper speed was 1100m.min^{-1} and the blade
10 angle was 44° . The solids concentration of each
coating composition was adjusted so that the pressure
of the hydraulic fluid supplied to a pressurisable tube
used for biasing the blade against the web of paper was
in the range of from 1.0 to 1.5 bar in order to provide
15 the desired coat weight. The dry weight of the coating
applied to the web of paper was in each case 6g.m^{-2} .
The coated paper was dried and then subjected to
calendering by passage ten times between the rolls of a
pilot-scale supercalender at a temperature of 80°C and
20 a linear pressure of 230kN.m^{-1} .

The samples of calendered coated paper were then
tested for gloss, brightness and Parker Print Surf by
the methods which were described in Example 3. Samples
were also tested for "% missing dots", or gravure print
25 quality, by the method described in Example 6 earlier.

The results obtained are set forth in Table 6 as
follows.

- 43 -

TABLE 6

Pigment	Gloss (TAPPI units)	% reflectance to light of 457nm wavelength	Parker Print Surf 1000 kPa	% missing dots
Composition 3	63	68.9	0.85	2.7
Composition 4	66	69.2	0.82	2.8
Composition 5	59	68.6	0.87	2.3

These results show that paper coated with
Compositions 3, 4 and 5 show good gloss and print
5 properties.

- 44 -

CLAIMS

1. A pigment product suitable for use in a coating composition to provide a gloss coating on paper, the
5 pigment product comprising a processed particulate kaolin whose particles have a particle size distribution such that at least 80% by weight of the particles have an equivalent spherical diameter less than $2\mu\text{m}$ and not less than 8% by weight of the
10 particles have an equivalent spherical diameter less than $0.25\mu\text{m}$ and whose particles have a shape factor of at least 45.
2. A pigment product as claimed in claim 1 and wherein at least 12% by weight of the particles of the
15 product have an equivalent spherical diameter less than $0.25\mu\text{m}$.
3. A pigment product as claimed in claim 1 and wherein at least 84% by weight of the particles have an equivalent spherical diameter less than $2\mu\text{m}$, and at
20 least 60% by weight of the particles have an equivalent spherical diameter less than $1\mu\text{m}$.
4. A pigment product as claimed in claim 1, claim 2 or claim 3 and wherein from 15% to 35% by weight of the particles have an equivalent spherical diameter less
25 than $0.25\mu\text{m}$.
5. A pigment product as claimed in any one of the preceding claims and wherein at least 50% by weight of the particles have an equivalent spherical diameter in the range of from $0.75\mu\text{m}$ to $0.25\mu\text{m}$.

- 45 -

6. A pigment product as claimed in any one of the preceding claims and wherein the mean equivalent spherical diameter of the particles of the product is from 0.3 μ m to 0.8 μ m.
- 5 7. A pigment product as claimed in any one of the preceding claims and wherein the shape factor of the particles of the pigment product is at least 50.
8. A pigment product as claimed in claim 7 and wherein the shape factor of the particles is from 55 to
- 10 65.
9. A method of producing a pigment product as claimed in any one of claims 1 to 8 and which method comprises the steps of:
- (a) mixing a raw or partially processed kaolin clay
- 15 with water to form an aqueous suspension;
- (b) subjecting the suspension produced by step (a) to attrition grinding using a particulate grinding medium by a process in which the average shape factor of the kaolin clay is increased by at least 10;
- 20 (c) separating the suspension of kaolin clay ground in step (b) from the particulate grinding medium; and
- (d) dewatering the suspension of ground kaolin clay separated in step (c) to recover a pigment product therefrom.
- 25 10. A method as claimed in claim 9 and wherein the kaolin clay employed in step (a) comprises a sedimentary kaolin clay.
11. A method as claimed in claim 10 and wherein the kaolin clay employed in step (a) consists of particles

- 46 -

having an equivalent spherical diameter such that not more than 40% by weight have an equivalent spherical diameter larger than $10\mu\text{m}$, and not more than 50% by weight have an equivalent spherical diameter less than $2\mu\text{m}$.

12. A method as claimed in claim 10 or claim 11 and wherein the particles of the kaolin clay in step (a) have a shape factor of not greater than 15.

13. A method as claimed in any one of claims 9 to 12 and wherein the method includes at least one additional treatment step.

14. A method as claimed in claim 13 and wherein the method includes between step (a) and step (b) an additional purification step comprising froth flotation or magnetic separation or both.

15. A method as claimed in claim 13 or claim 14 and wherein the additional treatment step includes liquid working following step (c) or step (d).

16. A method as claimed in claim 12, claim 13, claim 14 or claim 15 and wherein the method includes in the process of step (b) prior to the said grinding an additional comminution stage to provide delamination of the particles of the raw kaolin clay.

17. A method as claimed in claim 16 and wherein the additional comminution stage comprises wet grinding in a suspension containing not more than 40% by weight solids, the wet grinding being carried out using a particulate grinding medium under conditions in which no substantial vortex is set up in the suspension.

- 47 -

18. A method as claimed in claim 16 or claim 17 and wherein the energy dissipated during the additional comminution stage is less than 75kWh per tonne of kaolin present on a dry weight basis.
- 5 19. A method as claimed in any one of claims 9 to 18 and wherein in step (b) grinding following the additional comminution stage is carried out under conditions wherein a vortex is formed in the aqueous suspension treated.
- 10 20. A method as claimed in claim 19 and wherein in the grinding following the additional comminution stage the energy dissipated is from 40kWh to 120kWh per tonne of kaolin clay present on a dry weight basis.
21. A method as claimed in any one of claims 9 to 20
15 and wherein there is added from 99 to 50 parts by weight of the kaolin clay with from 1 to 50 parts by weight of a further kaolin clay having a shape factor of at least 15 and having at least 85% by weight of its particles smaller than $2\mu\text{m}$ and at least 20% by weight
20 of its particles smaller than $0.25\mu\text{m}$.
22. A method as claimed in claim 21 and wherein the further kaolin clay is added prior to step (b).
23. A method as claimed in claim 21 and wherein the further kaolin clay is added following step (c) or step
25 (d).
24. A coating composition for use in producing gloss coatings on paper and other substrates, which composition comprises an aqueous suspension of a particulate pigment together with a hydrophilic

- 48 -

adhesive, wherein the particulate pigment comprises a pigment product as claimed in any one of claims 1 to 8.

25. A composition as claimed in claim 24 and wherein the adhesive forms from 4% to 30% of the solids of the composition on a dry weight basis.

26. A composition as claimed in claim 23 or claim 24 and wherein the solids content of the composition is from 60% to 90% by weight of the composition.

27. A composition as claimed in any one of claims 24 to 26 and wherein at least 80 per cent by weight of the particulate pigment of the composition comprises the pigment product claimed in any one of claims 1 to 8.

28. A composition as claimed in any one of claims 24 to 27 and wherein the adhesive comprises a modified or unmodified starch.

29. A composition as claimed in any one of claims 24 to 28 and wherein the adhesive comprises a binder other than starch.

30. A method of use of the coating composition claimed in any one of claims 24 to 29 which comprises applying the composition to coat a sheet of paper and calendering the paper to form a gloss coating thereon.

31. A method of treating a kaolin clay to increase the particle fineness and shape factor thereof which includes the steps of:

(a) treating an aqueous suspension of the clay by a first comminution process to give delamination of the clay, in which an energy of not more than 75kWh per tonne of clay on a dry weight basis is dissipated;

- 49 -

(b) treating the clay after delamination in step (a) by a second comminution process to give particle comminution in which an energy of from 40 to 120kWh per tonne of clay on a dry weight basis is dissipated.

- 5 32. A method as claimed in claim 31 and wherein step (a) is carried out in a medium grinding mill in which no vortex is established and step (b) is carried out in a medium grinding mill in which a vortex is established.

INTERNATIONAL SEARCH REPORT

Int. l. Application No. PCT/GB 99/00888

A. CLASSIFICATION OF SUBJECT MATTER

D 21 H 17/68

According to International Patent Classification (IPC) or to both national classification and IPC 6

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

D 21 H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0245553 A2 (ENGELHARD CORPORATION) 19 November 1987, claims 1-19. --	1-32
A	DE 4213746 A1 (STORA FELDMÜHLE AG) 28 October 1993, claims 1-9. ----	1-32

☐ Further documents are listed in the continuation of box C.☐ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

21 June 1999

Date of mailing of the international search report

22 07 1999

Name and mailing address of the ISA

European Patent Office, P.O. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

BRUS e.h.

ANHANG

zum internationalen Recherchen-
bericht über die internationale
Patentanmeldung Nr.

ANNEX

to the International Search
Report to the International Patent
Application No.

ANNEXE

au rapport de recherche inter-
national relatif à la demande de brevet
international n°

PCT/GB 99/00888 SAE 229733

In diesem Anhang sind die Mitglieder
der Patentfamilien der im obenge-
nannten internationalen Recherchenbericht
angeführten Patentdokumente angegeben.
Diese Angaben dienen nur zur Unter-
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family
members relating to the patent documents
cited in the above-mentioned inter-
national search report. The Office is
in no way liable for these particulars
which are given merely for the purpose
of information.

La présente annexe indique les
membres de la famille de brevets
relatifs aux documents de brevets cités
dans le rapport de recherche inter-
national visée ci-dessus. Les renseigne-
ments fournis sont donnés à titre indica-
tif et n'engagent pas la responsabilité
de l'Office.

In Recherchenbericht angeführtes Patentdokument Patent document cited in search report Document de brevet cité dans le rapport de recherche	Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
EP A2	245553	19-11-1987	
		US A	4738726
		AT E	1016332
		AU A1	58925786
		AU B2	584713
		BR A	8603051
		CA A1	1285677
		CN A	86105012
		CN B	1008373
		DE C0	3689655
		DE T2	3689655
		EP A3	245553
		EP B1	245553
		ES A1	556670
		ES A5	556670
		ES A1	8707277
		ES A5	557317
		ES A1	557317
		ES A1	8801693
		FI A0	862632
		FI A	862632
		FI B	91177
		FI C	91177
		JP A2	62267371
		KR B1	9405836
DE A1	4213746	28-10-1993	
		AT E	158037
		DE C2	4213746
		DE C0	59307346
		EP A1	637352
		EP B1	637352
		ES T3	2108865
		FI A	944965
		FI A0	944965
		JP T2	7505927
		US A	5439558
		WO A1	9322560
			19-04-1988
			15-03-1994
			19-11-1987
			01-06-1989
			12-01-1988
			02-07-1991
			25-11-1987
			13-06-1990
			24-03-1994
			15-09-1994
			02-03-1988
			16-02-1994
			16-07-1987
			14-08-1987
			01-10-1987
			16-02-1988
			09-03-1988
			16-04-1988
			12-06-1986
			13-11-1987
			15-02-1994
			25-05-1994
			20-11-1987
			24-06-1994
			15-09-1997
			07-03-1996
			16-10-1997
			08-02-1995
			10-09-1997
			01-01-1998
			21-10-1994
			21-10-1994
			29-06-1995
			08-08-1995
			11-11-1993

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.